




	Membrane Element	LFC3-LD
Performance:	Permeate Flow:	11,000 gpd (41.6 m <sup>3</sup> /d)
	Salt Rejection: Nominal	99.7 %
Туре	Configuration: Membrane Polymer: Nominal Membrane Area:	Spiral Wound Composite Polyamide Neutrally charged 400 ft <sup>2</sup>
Application Data*		600 psig (4.16 MPa)
	Maximum Chlorine Concentration: Maximum Operating Temperature: Feedwater pH Range: Maximum Feedwater Turbidity: Maximum Feedwater SDI (15 mins): Maximum Feed Flow:	< 0.1 PPM 113 °F (45 °C) 3.0 - 10.0 1.0 NTU 5.0 75 GPM (17.0 m <sup>3</sup> /h)
	Minimum Ratio of Concentrate to Permeate Flow for any Element: Maximum Pressure Drop for Each Element:	5:1 10 psi

\* The limitations shown here are for general use. The values may be more conservative for specific projects to ensure the best performance and longest life of the membrane.

## **Test Conditions**

The stated performance is initial (data taken after 30 minutes of operation), based on the following conditions:



Notice: Permeate flow for individual elements may vary + or - 15 percent. All membrane elements are supplied with a brine seal, interconnector, and o-rings. Elements are vacuum sealed in a polyethylene bag containing less than 1.0% sodium meta-bisulfite solution, and then packaged in a cardboard box.

Hydranautics believes the information and data contained herein to be accurate and useful. The information and data are offered in good faith, but without guarantee, as conditions and methods of use of our products are beyond our control. Hydranautics assumes no liability for results obtained or damages incurred through the application of the presented information and data. It is the user's responsibility to determine the appropriateness of Hydranautics' products for the user's specific end uses. 6/29/05